

# PRODUCT DATA SHEET

## TOPCOAT ANTI-SLIP (ALL COLOURS)

“Topcoat Anti-Slip combines the traditional synthetic enamel, deep in colour, with synthetic granular material to leave a textured finish.”

### PRODUCT DESCRIPTION

Topcoat Anti-Slip is a traditional, ultra-high quality, coach enamel finish achieving a 90% gloss sheen level with a synthetic granular material added to provide a slip resistant finish.

It is a synthetic gloss enamel for brush and roller application, making it the perfect paint for Walkways, Roof and Cockpit areas. It is highly pigmented giving it excellent covering power. It also contains non-aggressive solvents making it the ideal choice over existing paint services. The quality allows longer maintenance intervals, extending life between repaints.

Topcoat Anti-Slip is available in Symphony Narrowboat Paint colours, RAL Classic, BS 4800, BS 391C and any colour you require.

### USES

Topcoat Anti-Slip provides an effective waterproof, anti-corrosive, protective coating. It is resistant to low concentrations of oil, alkalis and acids and can withstand prolonged oxidation and accumulation of water. It is suitable for application to a wide variety of metals including steel, iron, zinc and aluminium. It is perfect for flat areas of the narrowboat, above the waterline, from bow to stern where foot traffic is prevalent.

### CHARACTERISTICS / ADVANTAGES

- Slip Resistant Finish
- Premium Quality Mirror Finish
- Excellent UV Resistance
- Highly Pigmented
- Extended Gloss & Colour Retention






<b>Type of Paint</b>	Coach Enamel
<b>Flashpoint</b>	ca. 42°C
<b>Film Thickness Per Coat @ 12 m<sup>2</sup>/L</b>	Wet – 60 microns Dry – 35 microns
<b>Chemical And Water Resistance</b>	Resistant to: most salt solution, dilute acids and alkalis, oils, water and alcohol. Not resistant to: solvents and some detergent solutions

### PRODUCT INFORMATION









<b>Packaging</b>	1 Litre and 2.5 Litres
<b>Colours</b>	Symphony Narrowboat Paint Colours. Also available in RAL Classic, BS 4800, BS 391C and other colour schemes under code NBMIXANT. Please call for details.


## TECHNICAL INFORMATION

	Chemical Base	Solvent Based. Symphony Narrowboat Paint Topcoat Anti-Slip is made using an Alkyd Resin. Synthetic Anti-Slip beads are added to create the non-slip texture.
	Storage Conditions	Contains a flammable solvent, and all normal precautions against fire must be taken during both storage and use. Store in original container in cool (5°C - 25°C) dry conditions. Keep away from sources of ignition.
	Density	ca. 0.895 g/cm <sup>3</sup> at 20°C
	Viscosity	200 mPas
	VOC	380 g/l

## APPLICATION INFORMATION

	Consumption	10m <sup>2</sup> per litre		
	Ambient Air Temp	5°C - 40°C.		
	Drying Times @ 20°C			

### SUBSTRATE PREPARATION



Use Symphony Narrowboat Paint Anti-Slip over a wide variety of surfaces that have been suitably sanded, primed and undercoated. We recommend Symphony Narrowboat Paint Metal Primer and Symphony Narrowboat Paint Undercoat.

Remove loose or blistered paint and flat down existing surfaces with 320 Grit sanding. Remove sanding dust by wiping with a tack cloth.

Tape off edges using low tack masking tape.

### SUBSTRATE APPLICATION



Stir well prior to use. Apply the first coat to a DFT of 35 microns (+/- 5 microns). Apply evenly in 3ft sections by HD Foam Roller and if necessary laid off by Synthetic Brush. Leave to dry for a minimum of 24 hours before application of the second coat.

Minimum Total DFT after two coats of Metal Primer, three coats of Undercoat and three coats of Topcoat should be 200 microns. If required, add up to 10% Thinner 2611 or 2612 or 5% PPA brush additive to ease application. Avoid cold, damp or high humidity conditions.

## LIMITATIONS

- Do not use in areas where subsequent solvent contact is likely.
- Do not use for potable drinking water tanks.
- Avoid inhalation of vapours in confined spaces.
- Allow sufficient drying time between coats. Symphony Narrowboat Paint Topcoat Gloss may bleed through any paints subsequently applied over it. Apply a recommended primer and undercoat before overpainting.

## LOCAL RESTRICTIONS

Note that because of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local authority for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet (MSDS) containing physical, ecological, toxicological and other safety related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end use of Symphony Narrowboat Paint products, are given in good faith based on Symphony Coatings current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Symphony Coatings recommendations.

In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered.

The user of the product must test the product's suitability for the intended application and purpose. Symphony Coatings reserves the right to change the properties of its products.

The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

## CONTACT US

Symphony Coatings Group Ltd.  
10a Grange Way  
Whitehall Industrial Estate  
Colchester  
CO2 8HG

Telephone: 03333208821

Email: [hello@symphonynarrowboatpaint.co.uk](mailto:hello@symphonynarrowboatpaint.co.uk)